



Technical Specifications

PROPERTIES	UNIT	TARGET VALUES						
Grammage	g/m ²	80	90	105	112	125	140	150
Moisture	%	7.0	7.0	7.0	7.0	7.0	7.0	7.0
Bursting strength	kPa	180	195	225	260	300	320	350
SCT, CD	kN/m	1.4	1.5	1.8	1.9	2.2	2.4	2.5
CMT 30	N	160	170	200	210	220	240	250
Cobb (60 Sec)	g/m ²	30	30	30	30	30	30	30

PROPERTIES	UNIT	TEST STANDARD	TOLERANCES
Grammage	g/m ²	ISO : 536	± 3%
Moisture	%	ISO : 287	-50%
Bursting strength	kPa	ISO : 2758	-10%
SCT, CD	kN/m	ISO : 9895	-10%
CMT 30	N	ISO : 7263	-10%
Cobb (60 Sec)	g/m ²	ISO : 535	+20

Standard Test Conditions (ISO 187) : Temp 23± 1°C and Relative Humidity 50 ± 2%