

Technical Specifications

PROPERTIES	UNIT	TARGET VALUES			
Grammage	g/m ²	115	125	135	150
Moisture	%	4.5-7.0	4.5-7.0	4.5-7.0	4.5-7.0
Bursting strength	kPa	210-240	265-300	290-320	310-350
SCT, CD	kN/m	2.3	2.5	2.7	3.0
Cobb (60 Sec)	g/m ²	25-50	25-50	25-50	25-50
CMT 30	N	200-220	220-240	240-260	260-280

PROPERTIES	UNIT	TEST STANDARD	TOLERANCES
Grammage	g/m ²	ISO : 536	± 3%
Moisture	%	ISO : 287	± 1.5%
Bursting Strength	kPa	ISO : 2758	-10%
SCT, CD	kN/m	ISO : 9895	-10%
Cobb (60 Sec)	g/m ²	ISO : 535	≤ 50
CMT 30	N	ISO : 7263	-10%

Standard Test Conditions (ISO 187) : Temp 23± 1°C and Relative Humidity 50 ± 2%